



TECHNICAL REPORT

Toxicological Analysis of performance infill for synthetic turf fields according to *EN 71-3* standard

– Safety of toys Part 3: Migration of certain elements.

Lower Canada College.

Report Number **R14525CAN-B1**

Client
M. Paul Caron
Les Surfaces Carpell inc
745, Rue Vadnais,
Granby, QC, Canada

Date **November 5th 2014**

This report contains 3 pages in total.

It may not be used for commercial purposes, unless it is reproduced in its entirety.

LABOSPORT CANADA

5661, rue de Lanaudière, Suite 200, Montréal (Québec) H2G 3A5 CANADA
contact@labosport.ca
Tel. +1 514 277 9111 • Fax. +1 514 277 9112

www.labosport.ca

Toxicological Analysis of performance infill for synthetic turf fields according to EN 71-3 standard
– Safety of toys Part 3: Migration of certain elements.
Lower Canada College.



SUMMARY

Toxicology test according to **EN 71-3 - Safety of toys Part 3: Migration of certain elements (Material of Category III)** has been carried out on rubber sample collected at Lower Canada College synthetic turf field.

Abstract:

The EN 71-3 standard specifies maximum migration limits for three categories of (toy) materials. The limits for the migration of certain elements are expressed in milligrams per kilogram material and are detailed in the report. The purpose of the limits is to minimise children's exposure to certain potentially toxic elements. The EN 71-3 concerns all toys and materials that might be ingested.

Soluble elements are extracted from materials using conditions which simulate the material remaining in contact with gastric juices for a period of time after swallowing. The concentrations of the soluble elements are determined quantitatively by two different methods:

1. Method for determining general elements: Aluminium, Antimony, Arsenic, Barium, Boron, Cadmium, Chromium, Cobalt, Copper, Lead, Manganese, Mercury, Nickel, Selenium, Strontium, Tin and Zinc;
2. Method for determining Chromium (III) and Chromium (VI);

DESCRIPTION OF THE PRODUCT

Description of the product tested	PERFORMANCE INFILL FOR SYNTHETIC TURF FIELDS
Name of the product	SBR RUBBER – AMBIENT GROUND
Manufacturer	NOT SUBMITTED
Site	LOWER CANADA COLLEGE, MONTREAL, QC
Sample number	CAN0001465
Date of the tests	NOVEMBER 2014

REPORTED BY:

Mickaël Benetti, T.P.
(Lab Manager) - Writer

Guillaume Loubersac
(Director) - Approver

Report number	R14525CAN-B1	Page 2 / 3
Date	November 5th 2014	

Toxicological Analysis of performance infill for synthetic turf fields according to EN 71-3 standard
– Safety of toys Part 3: Migration of certain elements.
Lower Canada College.



IDENTIFICATION OF RUBBER SAMPLE CAN0001465

Parameter	Test method	Results	Product Declaration	Variation	Requirements	Pass/Fail
Size (mm)	EN933	0.8 – 2.5	0.5 – 2.0	-1 %	$\leq \pm 20\%$	Pass
Shape	prEN14955	Angular	Angular	Similar shape	Similar shape	Pass
Density (g/cm ³)	EN 1097	0.49	0.47	4 %	$\leq \pm 15\%$	Pass
TGA %org.	TGA	64.8	63.2	3 %	$\leq \pm 15\%$	Pass
TGA %inorg.	TGA	35.2	36.8	-4 %	$\leq \pm 15\%$	Pass

TOXICOLOGICAL ANALYSIS CAN0001465

Element	Units	Test method	Results	Requirements Category III	Pass/Fail
Aluminium	mg/kg MS	NF EN ISO 11885	45.3	70 000	Pass
Antimony	mg/kg MS	NF EN ISO 11885	n.d.*	560	Pass
Arsenic	mg/kg MS	NF EN ISO 11885	n.d.*	47	Pass
Barium	mg/kg MS	NF EN ISO 11885	3.43	18 750	Pass
Boron	mg/kg MS	NF EN ISO 17294-1 et 2	2.30	15 000	Pass
Cadmium	mg/kg MS	NF EN ISO 17294-1 et 2	n.d.*	17	Pass
Cobalt	mg/kg MS	NF EN ISO 11885	1.06	130	Pass
Copper	mg/kg MS	NF EN ISO 11885	4.73	7 700	Pass
Lead	mg/kg MS	NF EN ISO 11885	n.d.*	160	Pass
Manganese	mg/kg MS	NF EN ISO 11885	7.66	15 000	Pass
Mercury	mg/kg MS	NF EN ISO 17294-1 et 2	n.d.*	94	Pass
Nickel	mg/kg MS	NF EN ISO 11885	2.11	930	Pass
Selenium	mg/kg MS	NF EN ISO 11885	n.d.*	460	Pass
Strontium	mg/kg MS	NF EN ISO 17294-1 et 2	1.23	56 000	Pass
Tin	mg/kg MS	NF EN ISO 11885	n.d.*	180 000	Pass
Zinc	mg/kg MS	NF EN ISO 11885	532	46 000	Pass
Chromium III	mg/kg MS	NF T 90-043	n.d.*	460	Pass
Chromium VI	mg/kg MS	NF T 90-043	n.d.**	0.2	Pass

*Not detectable – substance could not be detected, the detection limit for the used test method is <0.5mg/kg MS

** Not detectable – substance could not be detected, the detection limit for the used test method is <0.2mg/kg MS

Report number	R14525CAN-B1	Page 3 / 3
Date	November 5th 2014	